
# **Product Overview**

**MOVING YOUR WORLD** 



## **NYEMED®** 7630

A biocompatible, paste-like grease for rolling and sliding components.



### **Advantages**

**Excellent resistance** to oxidation and moisture

Very wide temperature range (-50 to 175°C)

#### **Product Description**

A paste-like, synthetic hydrocarbon grease. Benefits include corrosion protection and wear reduction for sliding and rolling metal components, even at high temperatures and speeds.

#### ISO 13485:2016 Certified

Nye Lubricants, a member of the FUCHS Group, operates a Quality Management System that complies with the requirements of ISO 13485:2016. Our process controls, documentation, and quality standards meet or exceed all requirements for the design, manufacture, and distribution of synthetic lubricants for medical devices.

#### **Biocompatibility**

Test	Standard	Results	Meaning
Cytotoxicity L929 Agar Diffusion (Direct Contact)	ISO 109993-5	Grade 0	No Cellular Reactivity
Skin Irritation (Direct Contact)	ISO 10993-10	Primary Irritation Index 1.0	Slight Irritant
Acute Systemic Toxicity (Direct Injection)	ISO 10993-11	Negative	Pass

## **NYEMED®** 7630

Lubricants add value to innovative designs in medical technology every day. Our NYEMED® product line consists of biocompatible greases, oils, gels and fluids that were specifically formulated to enable, protect and improve the functionality of medical devices. In addition to biocompatibility testing, we also provide data on the typical properties of our lubricants.

#### **Properties**

Base Fluid Properties		Value	Test Method
Туре		Synthetic Hydrocarbon	
Flash Point		> 280°C	ASTM D92
Base Fluid Apparent Viscosity (cP)	25°C	112	Nye CTM
	45°C	44	

Product Properties		Typical Value	Test Method
Color/Appearance		Tan, Translucent	Visual
Apparent Viscosity (cP)	25 °C, 50/s shear rate	11,530	Nye CTM
Density (g/cm³)	25 °C	0.87	Nye CTM
NLGI Grade		2	ASTM D217
Oil Separation	24 h, 100 °C	0.5%	ASTM D6184
Evaporation	24 h, 100 °C	0.1%	ASTM D972

Typical Values are not indicative of a specification.

FUCHS LUBRICANTS CO. 17050 Lathrop Avenue Harvey, IL 60426 United States Phone + 1 708-333-8900 E-mail inquiry@fuchs.com www.fuchs.com/us FUCHS LUBRICANTS CANADA LTD. (Eastern Division) 405 Dobbie Drive Cambridge, Ontario N1R 5X9 Canada Phone +1 519-622-2040 E-mail inquiriesCA@fuchs.com www.fuchs.com/ca FUCHS LUBRICANTS CANADA LTD.
(Pacific Division)

19829 99A Avenue
Langley, British Columbia
V1M 3G4
Canada
Phone +1 604-888-1552
E-mail inquiriesCA@fuchs.com
www.fuchs.com/ca

LUBRICANTES
FUCHS DE MÉZ
Acceso C No.
Parque Indus
76120 Querés
Mexico
Phone + 52 (4
E-mail info@f

LUBRICANTES
FUCHS DE MÉXICO SA DE CV
Acceso C No. 101
Parque Industrial Jurica
76120 Querétaro, Qro.
Mexico
Phone + 52 (442) 2 38 91-00
E-mail info@fuchs.com.mx
www.fuchs.com/mx